

The MC/RS series is your material solution for applications requiring basic medical approvals such as ISO 10993-5. The series is characterized by its resealing properties. The compounds are translucent and can be colored in many different ways. The compounds are produced exclusively on a special medical unit.

Processing Method

Injection Molding, Extrusion

Color / RAL DESIGN

- Translucent

Typical applications

- Infusion stoppers
- Membranes
- Closures

Material advantages

- US DMF listed
- Resealing
- Adhesion to PP, PE
- Optimized compression set
- Sterilizable (autoclave 134°C, β -/ γ -radiation 2x35 kGy, EtO)
- Weldable (Ultrasonic)
- Free from animal ingredients
- KRAIBURG TPE Medical Service Package

Regulations / Approvals

- VDI 2017
- ISO 10993-5 (Cytotoxicity)

Storage life after delivery is 12 month at storage conditions like in a dry place at temperatures from 15 to 30°C away from heat and flame, avoid storage in open sunlight. Avoid contact with oxides of nitrogen during storage.

For further information and individual custom solutions please contact our customer service.

WALDKRAIBURG - GERMANY
KRAIBURG TPE GMBH & CO. KG
info@kraiburg-tpe.com
+49 8638 9810-0

SELANGOR / KUALA LUMPUR - MALAYSIA
KRAIBURG TPE TECHNOLOGY (M) SDN.BHD.
info-asia@kraiburg-tpe.com
+60 3 9545 6393

BUFORD, GA - UNITED STATES
KRAIBURG TPE CORPORATION
info-america@kraiburg-tpe.com
+1 678 584-5020

Disclaimer: The information provided in this documentation corresponds to our knowledge on the subject at the date of its publication and may be subject to revision as new knowledge and data becomes available. All values reported are typical values based on sample test results and are not a guarantee of performance. The responsibility to conduct testing to determine suitability of use for the particular process or end-use application remains with the customer.

Compound name	Color / RAL DESIGN	Hardness DIN ISO 7619-1 Shore A	Density DIN EN ISO 1183-1 g/cm ³	Tensile Strength ¹ DIN 53504/ISO 37 MPa	Elongation at Break ¹ DIN 53504/ISO 37 %	Tear Resistance ISO 34-1 Methode B (b) (Graves) N/mm	CS 72 h/23 °C DIN ISO 815-1 Method A %	CS 24 h/70 °C DIN ISO 815-1 Method A %	CS 24 h/100 °C DIN ISO 815-1 Method A %
TM3RST	Translucent	33	0.890	7.5	800	12.0	9	20	30
TM4RST	Translucent	43	0.890	9.0	850	14.0	11	23	30

¹Deviating from ISO 37 standard test piece S2 is tested with a traverse speed of 200 mm/min.

All values published in this data sheet are rounded average values.

Disclaimer: The information provided in this documentation corresponds to our knowledge on the subject at the date of its publication and may be subject to revision as new knowledge and data becomes available. All values reported are typical values based on sample test results and are not a guarantee of performance. The responsibility to conduct testing to determine suitability of use for the particular process or end-use application remains with the customer.